

USPOREDNA TABLICA NEHRĐAJUĆIH ČELIKA

STANDARD EN (EUROPA)	№	USA AISI	NJEMAČKA W.Nr.	ITALIJA UNI	FRANCUSKA ANFOR	JUS	ŠVEDSKA SIS	VELIKA BRITANIJA BSI
X10 CrNi 18-8	1.4310	301	1.4310	X 12 CrNi 1707	Z 11 CN 18-08	Č.4571	23 31	301 S 21
		302	1.4319	X 8 CrNi 1910	Z 12 CN 18-09			302 S 25
X8 CrNiS 18-9	1.4305	303	1.4305	X 10 CrNiS 1809	Z 8 CNF 18-09	Č.4590	23 46	303 S 21
X5 CrNi 18-10	1.4301	304	1.4301	X 5 CrNi 1810	Z 7 CN 18-09	Č.4580	23 32	304 S 15
X2 CrNiN 18-10	1.4311	304LN	1.4311	X 2 CrNiN 1811	Z 3 CN 18-10 Az	Č.45707	23 71	304 S 61
		304H		X 8 CrNi 1910				
X2 CrNi 18-9	1.4307	304L	1.4307		Z 3 CN 19-09		23 52	304 S 11
X2 CrNi 19-11	1.4306	304L	1.4306	X 2 CrNi 1811	Z 3 CN 18-10		23 52	304 S 11
X4 CrNi 18-12	1.4303	305	1.4303	X 8 CrNi 1812	Z 8 CN 18-12	Č.45702	23 33	305 S 19
X15 CrNiSi 20-12	1.4828	309	1.4828	X 16 CrNi 2314	Z 17 CNS 20-12	Č.4577		309 S 24
X12 CrNi 23-13	1.4833	309S	1.4833	X 6 CrNi 2314	Z 15 CN 23-13			
		310	1.4845	X 22 CrNi 2520				310 S 24
X8 CrNi 25-21	1.4845	310S	1.4845	X 6 CrNi 2520	Z 8 CN 25-20		23 61	310 S 16
X15 CrNiSi 25-21	1.4841	314	1.4841	X 16 CrNiSi 2520	Z 15 CNS 25-20	Č.4578		
X5 CrNiMo 17-12-2	1.4401	316	1.4401	X 5 CrNiMo 1712	Z 7 CND 17-11-02	Č.4573	23 47	316 S 31
X3 CrNiMo 17-13-3	1.4436	316	1.4436	X 5 CrNiMo 1713	Z 7 CND 17-12-02	Č.45706	23 43	316 S 33
		316F	1.4427					
		316N						
		316H		X 8 CrNiMo 1712				
		316H		X 8 CrNiMo 1713				
X2 CrNiMo 17-12-2	1.4404	316L	1.4404	X 2 CrNiMo 1712	Z 3 CND 17-11-02	Č.45707	23 48	316 S 11
X2 CrNiMo 18-14-3	1.4435	316L	1.4435	X 2 CrNiMo 1713	Z 3 CND 18-14-03	Č.45704	23 53	316 S 13
X6 CrNiMo 17-12-2	1.4571	316Ti	1.4571	X 6 CrNiMoTi 1712	Z 6 CNDT 17-12	Č.4574	23 50	320 S 31
X2 CrNiMo 18-15-4	1.4438	317L	1.4438	X 2 CrNiMo 1815	Z 3 CND 19-15-04	Č.45705	23 67	317 S 12
X6 CrNiTi 18-10	1.4541	321	1.4541	X 6 CrNiTi 1811	Z 6 CNT 18-10	Č.4572	23 37	321 S 31
X10 CrNiTi 18-10	1.4878	321H	1.4878	X 8 CrNiTi 1811	Z 6 CNT 18-10		23 37	321 S 20
X6 CrNiNb 18-10	1.4550	347	1.4550	X 6 CrNiNb 1811	Z 6 CNNB 18-10	Č.4582	23 38	347 S 31
X13 NiCrSi 35-16	1.4864	330	1.4864		Z 20 NCS 33-16	Č.4579		
X3 CrNiMoN 27-5-2	1.4460	329	1.4460		Z 5 CND 27-05 Az		23 24	
X6 CrAl 13	1.4002	405	1.4002	X 6 CrAl 13	Z 8 CA 12	Č.49702		405 S 17
X2 CrTi 12	1.4512	409	1.4512	X 2 CrTi 12	Z 3 CT 12			409 S 19
X6 Cr 13	1.4000	410S	1.4000	X 6 Cr 13	Z 8 C 12	Č.4170	23 01	403 S 17
X6 Cr 17	1.4016	430	1.4016	X 8 Cr 17	Z 8 C 17	Č.4174	23 20	430 S 17
X6 CrMoS 17	1.4105	430F	1.4105	X 10 CrS 17	Z 8 CF 17	Č.47701		
X6 CrMo 17-1	1.4113	434	1.4113	X 8 CrMo 17	Z 8 CD 17-01			434 S 17
X3 CrTi 17	1.4510	439	1.4510	X 6 CrTi 17	Z 4 CT 17	Č.49701		
X18 CrN 28	1.4749	446	1.4749	X 16 Cr 26			23 22	
X12 Cr 13	1.4006	410	1.4006	X 12 Cr 13	Z 10 C 13	Č.41701	23 02	410 S 21
X12 CrS 13	1.4005	416	1.4005	X 12 CrS 13	Z 11 CF 13		23 80	416 S 21
X20 Cr 13	1.4021	420	1.4021	X 20 Cr 13	Z 20 C 13	Č.4172	23 03	420 S 29
X30 Cr 13	1.4028	420	1.4028	X 30 Cr 13	Z 33 C 13	Č.4173	23 04	420 S 45
X39 Cr 13	1.4031	420	1.4031		Z 33 C 13	Č.41731	23 04	420 S 45
X46 Cr 13	1.4034	420	1.4034	X 40 Cr 14	Z 44 C 14	Č.4175		
X17 CrNi 16-2	1.4057	431	1.4057	X 16 CrNi 16	Z 15 CN 16-02	Č.4570	23 21	431 S 29
X70 CrMo 15	1.4109	440A	1.4109		Z 70 C 15			
X90 CrMoV 18	1.4112	440B	1.4112			Č.4772		
X105 CrMo 17	1.4125	440C	1.4125					